

Bello
group A

Note: Photographic fabric scans are not colour accurate.
Always request actual fabric samples before ordering.



003




016



020



065



036



345



055




605



600




620




901



270



300



120




410



220



242



322



417



427



527



515

Bello

Product information

Bello is a unique upholstery material and it has shining and elegant appearance. It is a symbol of purity and it has been used in textiles for many years.

Technical information

EN	D	F	ES
Composition 18% Polyester, 80% PVC, 2% Polyurethane	Zusammensetzung 18% Polyester, 80% PVC, 2% Polyurethan	Composition 18% Polyester, 80% PVC, 2% Polyuréthane	Composición 18% Poliéster, 80% PVC, 2% Poliuretano
Tensile Strength >300 N / >300 N (ISO 1421)	Zerreifestigkeit >300 N / >300 N (ISO 1421)	Résistance à la traction >300 N / >300 N (ISO 1421)	Resistencia a la tracción >300 N / >300 N (ISO 1421)
Tear Strength >25 / >35 (ISO 46742)	Reifestigkeit >25 / >35 (ISO 46742)	La résistance au déchirement >25 / >35 (ISO 46742)	Resistencia al desgarre >25 / >35 (ISO 46742)
Elongation At Break 100±20% / 85±20% (ISO 1421)	Bruchdehnung 100±20% / 85±20% (ISO 1421)	Allongement à la rupture 100±20% / 85±20% (ISO 1421)	Alargamiento a la rotura 100±20% / 85±20% (ISO 1421)
Weight 500 gr/m2 (ISO 2686-2)	Gewicht 500 gr/m2 (ISO 2686-2)	Poids 500 gr/m2 (ISO 2686-2)	Peso 500 gr/m2 (ISO 2686-2)
Thickness 0.95 mm (ISO 2686-3)	Dicke 0.95 mm (ISO 2686-3)	Épaisseur 0.95 mm (ISO 2686-3)	Espesor 0.95 mm (ISO 2686-3)
Width 140 cm	Breite 140 cm	Largeur 140 cm	Ancho 140 cm
Abrasion Resistance >22,000 Martindale Cycles (DIN 53863)	Scheuerfestigkeit >22,000 Martindale Fahrräder (DIN 53863)	Résistance à l'abrasion >22,000 Martindale Cycles (DIN 53863)	Resistencia a la abrasión >22,000 Martindale Ciclos (DIN 53863)
Flexometer >100,000 FLX (ISO 7854)	Flexometer >100,000 FLX (ISO 7854)	Flexometer >100,000 FLX (ISO 7854)	Flexómetro >100,000 FLX (ISO 7854)
Light Fastness (Light Colors / Dark Colors) >3.00 BW / >5.00 BW (ISO 105B02)	Lichtechtheit (Helle/Dunkle Farben) >3.00 BW / >5.00 BW (ISO 105B02)	Solidité à la lumière (Couleurs Claires/Sombres) >3.00 BW / >5.00 BW (ISO 105B02)	Solidez a la luz (Colores Claros/Oscuros) >3.00 BW / >5.00 BW (ISO 105B02)
Color Fastness (Wet / Dry) >4 GS / >4 GS (ISO 105X12)	Farbechtheit (Nass/Trocken) >4 GS / >4 GS (ISO 105X12)	Solidité de la couleur (Mouillé/ Sec) >4 GS / >4 GS (ISO 105X12)	Rapidez del color (Húmedo/ Seco) >4 GS / >4 GS (ISO 105X12)