

Miura
group E

Note: Photographic fabric scans are not colour accurate.
Always request actual fabric samples before ordering.



113



221



266



244



128



261



281



374



373



358



324



159



144



392



518



299



641



921

Miura

Product information

Miura is an exquisitely soft natural leather. This stylish product with a pigmented grain-effect finish is virtually maintenance free, with a water based sealant for added protection.

Technical information

EN	D	F	ES
Composition 100% Genuine Leather	Zusammensetzung 100% Echtleder	Composition 100% Cuir véritable	Composición 100% Piel Genuina
Thickness 1.0 - 1.2mm	Dicke 1.0 - 1.2mm	Épaisseur 1.0 - 1.2mm	Espesor 1.0 - 1.2mm
Color Fastness to rubbing (Dry/Wet) 4-5 (UNI EN ISO 11640)	Reibechtheit (Trocken/Nass) 4-5 (UNI EN ISO 11640)	Solidité des couleurs au frottement (Sec/Mouillé) 4-5 (UNI EN ISO 11640)	Solidez del color al frotamiento (Seco/Húmedo) 4-5 (UNI EN ISO 11640)
Flex resistance ≥ 40,000 Martindale Cycles (BS EN ISO 5402)	Biegefestigkeit ≥ 40,000 Martindale Fahrräder (BS EN ISO 5402)	Résistance à la flexion ≥ 40,000 Martindale Cycles (BS EN ISO 5402)	Resistencia a la flexión ≥ 40,000 Martindale Ciclos (BS EN ISO 5402)
Tear Strength 44.40 N (BS EN ISO 3377-2)	Reißfestigkeit 44.40 N (BS EN ISO 3377-2)	La résistance au déchirement 44.40 N (BS EN ISO 3377-2)	Resistencia al desgarre 44.40 N (BS EN ISO 3377-2)
Finish Adhesion 5.48 N/cm (UNI EN ISO 11664)	Finish Haftung 5.48 N/cm (UNI EN ISO 11664)	Adhésion de finition 5.48 N/cm (UNI EN ISO 11664)	Acabado adhesivo 5.48 N/cm (UNI EN ISO 11664)
Color fastness to light 5 (UNI EN ISO B02)	Farbechtheit gegen Licht 5 (UNI EN ISO B02)	Solidité des couleurs à la lumière 5 (UNI EN ISO B02)	Solidez del color a la luz 5 (UNI EN ISO B02)
Tensile strenght 13.89 N/mm	Zerreißfestigkeit 13.89 N/mm	Résistance à la traction 13.89 N/mm	Resistencia a la tracción 13.89 N/mm
Elongation 40.57% (BS EN ISO 3376)	Bruchdehnung 40.57% (BS EN ISO 3376)	Allongement 40.57% (BS EN ISO 3376)	Alargamiento 40.57% (BS EN ISO 3376)
Elongation at 100 N 26.98% (BS EN ISO 3376)	Dehnung bei 100 N 26.98% (BS EN ISO 3376)	Allongement à 100 N 26.98% (BS EN ISO 3376)	Alargamiento a 100 N 26.98% (BS EN ISO 3376)
Bleaching Strength (Alcohol/Ammonia) 5/4-5	Bleichfestigkeit (Alkohol/ Ammoniak) 5/4-5	Résistance à la décoloration (De l'alcool/ Ammoniac) 5/4-5	Resistencia a la decoloración (Alcohol/ Amoníaco) 5/4-5
Aging 4-5 (ISO 17228-7B)	Altern 4-5 (ISO 17228-7B)	Vieillessement 4-5 (ISO 17228-7B)	Envejecimiento 4-5 (ISO 17228-7B)
Flame resistance Pass - BS 5852:1976 Part 1 Cigarette & Match	Flammenschutz Pass - BS 5852:1976 Part 1 Zigarettentest & Streichholztest	Résistance à la flamme Pass - BS 5852:1976 Part 1 Cigarette & Allumette	Resistencia al fuego Pass - BS 5852:1976 Part 1 Cigarrillo & Cerilla

