

Remix 2

group 6

Remix 2
group 6



113




223



242



233




923



912




942



842



422




443




452




823




733



743




762




773




753



852



123



133



143




163




152

Note: Photographic fabric scans are not colour accurate.
Always request actual fabric samples before ordering.



543




643




612




682



632



662



672




362



973



373



393



873



692

Remix 2

Product information

Remix is a woolen upholstery fabric made from thin and strong wool. The yarns used in Remix create threads consisting of three different colours and for each colourway, two different threads are used.

This combination creates a unique affect where the colours play across the surface of the fabric. The colour range spreads from bright colours to natural shades of earth tones.

Technical information

EN	D	F	ES
Composition 90% New Wool, 10% Nylon	Zusammensetzung 90% Schurwolle, 10% Nylon	Composition 90% Laine Vierge, 10% Nylon	Composición 90% Lana Virgen, 10% Nylon
Yarn type Staple, worsted	Garntyp Faser, Kammgarn	Type de fil Fibre, peigné	Tipo de hilo Fibra, estambre
Width 138 cm	Breite 138 cm	Largeur 138 cm	Ancho 138 cm
Weight 300 gr/m2	Gewicht 300 gr/m2	Poids 300 gr/m2	Peso 300 gr/m2
Flammability EN 1021-1/2 BS 5852, ignition source 2-3 Önorm B1/Q1 NF D 60 013 UNI 9175, 1IM AS/NZS 3837 class 2 Cal. Tech. Bull. 117, Sec. E IMO A.652(16) Crib 5 and B2 when flame protected No use of brominated flame retardants	Feuersicherung EN 1021-1/2 BS 5852, zündquelle2-3 Önorm B1/Q1 NF D 60 013 UNI 9175, 1IM AS/NZS 3837 Klasse 2 Cal. Tech. Bull. 117, Sec. E IMO A.652(16) Crib 5 und B2 Wenn die flammgeschützte Kein Einsatz bromierter Flammenschutzmittel	Flammabilité EN 1021-1/2 BS 5852, source d'inflammation 2-3 Önorm B1/Q1 NF D 60 013 UNI 9175, 1IM AS/NZS 3837 classe 2 Cal. Tech. Bull. 117, Sec. E IMO A.652(16) Crib 5 et B2 Quand protégé contre la flamme Pas d'utilisation de retardateurs de flamme bromés	Inflamabilidad EN 1021-1/2 BS 5852, fuente de ignición2-3 Önorm B1/Q1 NF D 60 013 UNI 9175, 1IM AS/NZS 3837 clase 2 Cal. Tech. Bull. 117, Sec. E IMO A.652(16) Crib 5 y B2 Cuando protegido contra la llama No uso de retardantes de llama bromados
Light Fastness Note 5-7 (ISO 105-B02)	Lichtechtheit Note 5-7 (ISO 105-B02)	Solidité à la lumière Note 5-7 (ISO 105-B02)	Solidez a la luz Note 5-7 (ISO 105-B02)
Pilling Note 3-4 (EN ISO 12945)	Pilling Note 3-4 (EN ISO 12945)	Boulochage Note 3-4 (EN ISO 12945)	Pilling Note 3-4 (EN ISO 12945)
Abrasion Resistance 100,000 Martindale Cycles (EN ISO 12947)	Scheuerfestigkeit 100,000 Martindale Fahrräder (EN ISO 12947)	Résistance à l'abrasion 100,000 Martindale Cycle (EN ISO 12947)	Resistencia a la abrasión 100,000 Martindale Ciclos (EN ISO 12947)
Cleaning Vacuuming and dry cleaning.	Reinigung Staubsaugen und chemische Reinigung.	Nettoyage Aspiration et nettoyage à sec.	Limpieza Aspiradora y limpieza en seco.